



 **EPC**
EUROPEAN
PORCELAIN
& CERAMICS

Porcelain Tiles
CALACATTA

Size & Shade

61.5X61.5cm / 24"X24"

Gloss - CALACATTA 61.5X61.5 WHITE
 Matt - CALACATTA-M 61.5X61.5 WHITE

30.7X61.5cm / 12"X24"

Gloss - CALACATTA 30.7X61.5 WHITE
 Matt - CALACATTA-M 30.7X61.5 WHITE

45.2X45.2cm / 18"X18"

Gloss - CALACATTA 45.2X45.2 WHITE


60X60cm / 24"X24" RECTIFIED

Gloss - CALACATTA 60X60 WHITE# C@B
 Matt - CALACATTA-M 60X60 WHITE# C@B


29,8X60 / 12"X24" RECTIFIED

Gloss - CALACATTA 29,8X60 WHITE# C@B
 Matt - CALACATTA-M 29,8X60 WHITE# C@B


mosaic



Gloss - MALLA CALACATTA
 Matt - MALLA CALACATTA-M
 30X30 / 12"X12"
 WHITE
 mosaics 7X7cm / 3"X3"



Matt - MALLA CALACATTA M
 12X12 / 12"X12"
 WHITE# C@B
 mosaics 5X5cm / 2"X2"




Matt - MALLA CALACATTA M
 8" X 8" / 20.3" X 20.3"
 WHITE# C@B
 mosaics 7X, cm / 8, "X3.2"

bullnose



Gloss - RODAPIE CALACATTA
 WHITE
 7X30.7cm / 3"X12"
 Matt - RODAPIE CALACATTA-M
 WHITE# C@B
 7X30.7cm / 3"X12"

PROFILE-M SILVER# C@B
 1X60cm / 0,4"X24"



V2

V1: Uniform appearance
V2: Slight Variation
 V3: Moderate Variation
 V4: Substantial Variation
 RANDOM PRODUCTION
 DESIGN AVAILABLE 4M2



Technical features

CHARACTERISTICS	Water Absorption	Breaking strength	Modulus of Rupture	Surface Abrasion Resistance (PEI)	Frost Resistance	Acids and Alkalis Resistance	Staining Resistance	Mohs Hardness	Slipperiness		
									TEST METHOD	STANDARD VALUE	TEST METHOD
ISO 10545-3 ASTM C373	ISO 10545-4 ASTM C648	ISO 10545-4 ASTM C482	ISO 10545-7	ISO 10545-12 ASTM C1026	ISO 10545-13 ASTM C650	ISO 10545-14	EN 101	ASTM C1028-96 SCOF	ANSI A137.1: 2012 DCOF	UNE-ENV -12633	
EB ≤ 0,5%	S ≥ 1300 N > 500lb	R ≥ 35N/mm² > 200psi	PEI	Required	Test method available	Minimum Class 3	Mohs Scale	The ITC identifies Tile Slip Resistant when SCOF ≥ 0,60	Required value min. of 0,42 for commercial areas likely to be wet		
307X615X10mm 12X24X0,4 in GLOSS	0.5% < E ≤ 3 %	pass	pass	III	pass	GLA / GLA	class 5	4	-	-	class 0
307X615X10mm 12X24X0,4 in MATT	EB ≤ 0,5%	pass	pass	IV	pass	GLA / GLA	class 5	5	0,72W / 1,025D	0,71W	class 0
615X615X10mm 24X24X0,4 in GLOSS	0.5% < E ≤ 3 %	pass	pass	III	pass	GLA / GLA	class 5	4	-	-	class 0
615X615X10mm 24X24X0,4 in MATT	EB ≤ 0,5%	pass	pass	IV	pass	GLA / GLA	class 5	5	0,72W / 1,025D	0,71W	class 0
298X600X10mm 12X24X0,4 in GLOSS	0.5% < E ≤ 3 %	pass	pass	III	pass	GLA / GLA	class 5	4	-	-	class 0
298X600X10mm 12X24X0,4 in MATT	EB ≤ 0,5%	pass	pass	IV	pass	GLA / GLA	class 5	5	0,72W / 1,025D	0,71W	class 0
600X600X10mm 24X24X0,4 in GLOSS	0.5% < E ≤ 3 %	pass	pass	III	pass	GLA / GLA	class 5	4	-	-	class 0
600X600X10mm 24X24X0,4 in MATT	EB ≤ 0,5%	pass	pass	IV	pass	GLA / GLA	class 5	5	0,72W / 1,025D	0,71W	class 0



Gloss - CALACATTA 29,8X60 ; C@B
Matt - CALACATTA-M 29,8X60 ; C@B



WHITE