



# FARO-R CENIZA - 14,4x89,3

Model: FARO-R CENIZA

Size: 14,4x89,3 cm

Thickness: 10 mm

Material type: PORCELAIN



Technical Characteristics		Reference standard
Manufacture process	Single-firing	Dry pressed ceramic tile
Thickness (mm.)	10	UNE EN ISO 10545 Part 2
Length, width, thickness, side straightness, orthogonality, flatness.	Conforms to the requisites applicable to each model as defined in standard UNE-EN 14411 for Group B Ia	UNE EN ISO 10545 Part 2
Water absorption	$E < 0,5 \%$	UNE EN ISO 10545 Part 3
Flexion resistance N/sq. mm. and breaking strength	$> 35$ $> 1300$	UNE EN ISO 10545 Part 4
Resistance to surface abrasion (Glazed tiles)	4	UNE EN ISO 10545 Part 7
Lineal thermic dilatation	$< 9 \cdot 10^{-6} / ^\circ \text{C}$	UNE EN ISO 10545 Part 8
Thermic impact resistance	It stands the test	UNE EN ISO 10545 Part 9
Cracking resistance	It stands the test	UNE EN ISO 10545 Part 11
Frost resistance	It stands the test	UNE EN ISO 10545 Part 12
Slip resistance	Class 1	UNE ENV 12633:2003
Inclined plane, wearing shoes	R9	DIN 51130

Chemical resistance		
Domestic cleaning products	Type GA	UNE EN ISO 10545 Part 13
Swimming pool salt	Type GA	
Acids and bases (low concentration)	Minimum Type GLB	
Stains resistance	Minimum Type 4	UNE EN ISO 10545 Part 14



Interlocked laying maximum 25%

< 25%

IMPORTANT: before fixing tiles, please check the shade, calibre and choice. Claims regarding these items cannot be accepted once the material has been fixed. A minimum joint of 1 to 2 mm is required. Document with commercial information and cannot be used either judicially or administratively without the express permission of VIVES Azulejos y Gres S.A.

The color of the tile of this data sheet is for guidance only and may differ from the actual tile color.



# FARO-R TIERRA - 14,4x89,3

Model: FARO-R TIERRA

Size: 14,4x89,3 cm

Thickness: 10 mm

Material type: PORCELAIN



Technical Characteristics		Reference standard
Manufacture process	Single-firing	Dry pressed ceramic tile
Thickness (mm.)	10	UNE EN ISO 10545 Part 2
Length, width, thickness, side straightness, orthogonality, flatness.	Conforms to the requisites applicable to each model as defined in standard UNE-EN 14411 for Group B Ia	UNE EN ISO 10545 Part 2
Water absorption	$E < 0,5 \%$	UNE EN ISO 10545 Part 3
Flexion resistance N/sq. mm. and breaking strength	$> 35$ $> 1300$	UNE EN ISO 10545 Part 4
Resistance to surface abrasion (Glazed tiles)	4	UNE EN ISO 10545 Part 7
Lineal thermic dilatation	$< 9 \cdot 10^{-6} / ^\circ \text{C}$	UNE EN ISO 10545 Part 8
Thermic impact resistance	It stands the test	UNE EN ISO 10545 Part 9
Cracking resistance	It stands the test	UNE EN ISO 10545 Part 11
Frost resistance	It stands the test	UNE EN ISO 10545 Part 12
Slip resistance	Class 1	UNE ENV 12633:2003
Inclined plane, wearing shoes	R9	DIN 51130

Chemical resistance		
Domestic cleaning products	Type GA	UNE EN ISO 10545 Part 13
Swimming pool salt	Type GA	
Acids and bases (low concentration)	Minimum Type GLB	
Stains resistance	Minimum Type 4	UNE EN ISO 10545 Part 14



Interlocked laying maximum 25%

< 25%

IMPORTANT: before fixing tiles, please check the shade, calibre and choice. Claims regarding these items cannot be accepted once the material has been fixed. A minimum joint of 1 to 2 mm is required. Document with commercial information and cannot be used either judicially or administratively without the express permission of VIVES Azulejos y Gres S.A.

The color of the tile of this data sheet is for guidance only and may differ from the actual tile color.