

Sample Type: **25x75 R WHITE BODY**

Sample Type: **WAVE**

Tests to be performed: Physical Tests

## RESULTS

	<u>Application Standard</u>
<b>WATER ABSORPTION</b> ..... 15,6%	UNE-EN-ISO 10545-3
<b>RESISTANCE TO LOW CONCENTRATIONS OF ACIDS</b>	UNE-EN-ISO 10545-13
HYDROCHLORIC ACID 3% ..... Class GLA	
<b>RESISTANCE TO HIGH CONCENTRATIONS OF ACIDS</b>	UNE-EN-ISO 10545-13
HYDROCHLORIC ACID 18% ..... Class GHA	
<b>RESISTANCE TO LOW CONCENTRATIONS OF ALKALIS</b>	UNE-EN-ISO 10545-13
POTASSIUM HIDROXIDE (30 g/l) ..... Class GLA	
<b>RESISTANCE TO HIGH CONCENTRATIONS OF ALKALIS</b>	UNE-EN-ISO 10545-13
POTASSIUM HIDROXIDE (100 g/l) ..... Class GHA	
<b>RESISTANCE TO CLEANING PRODUCTS</b>	UNE-EN-ISO 10545-13
AMMONIUM CHLORIDE (100 g/l) ..... Class GA	
SODIUM HYPOCHLORITE (20mg/l)..... Class GA	
<b>STAIN RESISTANCE</b>	UNE-EN-ISO 10545-14
Cr2O3 LIGHT OIL 40%(m/m) ..... Class 5	
IODINE (ALCOHOLIC SOL. 13 g/l) ..... Class 5	
OLIVE OIL ..... Class 5	
<b>SCRATCH HARDNESS OF SURFACE (MOHS)</b> ..... 5	UNE-EN 101