













TECHNICAL SPECIFICATIONS	
QUALITY LABORATORY	
MODEL	CALACATTA-P WHITE / GOLD 90x90cm / 36x36" - 60X12cm/24x48"

BODY TYPE	PORCELAIN Group Bla - POLISHED
-----------	--------------------------------

	Body Technical Specifications	TEST METHOD	Standard Value	Pass/Fail
	Length and Width	ISO 10545-2 ASTM C499	+/- 0.6 %	PASS
	Thickness	ISO 10545-2 ASTM C499	+/- 5 %	PASS
	Straightness of sides	ISO 10545-2 ASTM C485	+/- 0.5 %	PASS
	Surface Planarity	ISO 10545-2 ASTM C485	+/- 0.5 %	PASS
	Squareness/Rectangularity	ISO 10545-2 ASTM C502	+/- 0.6 %	
	Water Absorption	ISO 10545-3 ASTM C373	EB ≤ 0.5 %	PASS
	Modulus of Rupture	ISO 10545-4 ASTM C648	S ≥ 1300 N > 500lbf	PASS
	Bending Strength	ISO 10545-4 ASTM C482	R ≥ 35 N/mm ² > 200psi	PASS
	Frost Resistance	ISO 10545-12 ASTM C1026	RESIST	PASS
	Linear Thermal Expansion Coefficient	ISO 10545-8 ASTM C372	9*10 ⁻⁶ K ⁻¹ max.	PASS

	Technical Specifications of Surface	TEST METHOD	Standard Value	Pass/Fail
	Slipperiness	UNE-ENV-12633	CLASS 0	PASS
	Surface Abrasion Resistance (PEI)	ISO 10545-7	IV	PASS
	Surface Hardness (MOHS Scale)	UNE 67-101	4	PASS
	Acids and Alkalis Resistance	ISO 10545-13 ASTM C650	GLB/GLB	PASS
	Crazing resistance	ISO 10545-11	RESIST	PASS
	Staining Resistance	ISO 10545-14 ASTM CTI 81-7	5	PASS
	Surface Quality	ISO 10545-2	>95 % OK	PASS

GOODS ARE IN CONFORMITY WITH ISO 13006 STANDARDS